



VAG A T E X [®]
I T A L I A

TECHNICAL SHEET

(according to the standard UNI EN ISO 14465)

ARTICLE:	VGT 2787 TF ACC/OUTDOOR STRETCH - MÉRIDIEN MATELASSÉ
COMPOSITION:	50%PC 45%PL 5%EA
WEIGHT G/M LIN.:	: 950 gr/mtl
REPEAT(WARP/WEFT):	no
METERS PER ROLL:	25 mt
WIDHT CM:	140

REGULAR CARE AND LEGAL GUARANTEE:

Regular cleaning is important to keep the upholstery fabric looking its best and to extend its life. The guarantee is subject to the correct use of the fabric and its maintenance.

It is usually recommended that upholstered furniture with normal commercial use should be cleaned 2-3 times a year.

Upholsteries in private households usually need less frequent cleaning. In order to ensure satisfying cleaning results, we recommend to contact a professional cleaning institute.

Please follow the maintenance instructions of the technical data sheet.



- Abrasion Resistance - Martindale UNI EN ISO 12947-2 + EN 14465, appendice A	Color degradation after 3000 giri: 4 Color degradation after 6000 giri: 4 END POINT (rubs): 20.000
Pilling resistance by the modified martindale method UNI EN ISO 12945-2	Degradation average photographic scale 1/5 : 3/4 At 2000 rubs: 3/4
Dimensional change after washing UNI EN ISO 6330	Narrowing (weft): + - 3% Shortening (warp): + - 3%
Dimensional change after dry cleaning UNI EN ISO 3175	Narrowing (weft): $\leq \pm 3\%$ Shortening (warp): $\leq \pm 3\%$
Resistance to yarn Slippage at stitched seams UNI EN ISO 13937-3 (din 14465)	Weft mm < 6 warp mm < 6
Fire Resistance	BS5852 match + cigarette (with foulard treatment) TB 117 (with foulard treatment)
Environmental benefits	<ul style="list-style-type: none"> - No use of AZO dyes, which may split off carcinogenic acrylic amines. - No use of dyes containing heavy metals/complies with ETAD norm. - No use of brominated flame retardants. - Complies with REACH regulation.
Sustainability	ECO-PATH AVAILABLE
Available teflon treatment	(on request)
Type of finish used	EXCLUSIVE FINISH FOR STRETCH ITEM
Tariff code	6004900000
Raw Material & Weaving	Made in Italy



Azione meccanica ridotta + asciugare appeso



MADE IN ITALY

www.vagatexitalia.it





OUTDOOR FABRIC

TEST	U.M	RESULT	PROCEDURE
3015001 Colour Fastness - Luce Artificiale			UNI EN ISO 105 B02:2014
Colour change	1/8	6/7	
3008011 Colour Fastness - Crocking dry and wet A			UNI EN ISO 105 X12:2016
Wales - Dry		4 - 5	
Wales - Wet		4 - 5	
Courses - Dry		4 - 5	
Courses - Wet		4 - 5	
3018011 Colour Fastness - Artificial weathering			UNI EN ISO 105 B04:2000
Method		2	
Evaluation	1/8	6/7	
30044011 Colour Fastness - Sea water A			UNI EN ISO 105 E02:2013
Colour change		5	
Staining on - AC		4 - 5	
Staining on - CO		4 - 5	
Staining on - PA		4 - 5	
Staining on - PL		4 - 5	
Staining on - PC		4 - 5	
Staining on - WO		4 - 5	
3005001 Colour Fastness - Chloride water			UNI EN ISO 105 E03:2010
pH test solution		7,5	
Cl ₂ active	mg/l	100	
Colour change		4 - 5	
3006011 Colour Fastness - Acide Perspiration A			UNI EN ISO 105 E04:2013
Colour change		5	
Staining on - AC		4	
Staining on - CO		4	
Staining on - PA		3/4	
Staining on - PL		4	
Staining on - PC		4	
Staining on - WO		4	
3007001 Colour Fastness - Alkaline Perspiration A			UNI EN ISO 105 E04:2013
Colour change		5	
Staining on - AC		4	
Staining on - CO		4	
Staining on - PA		4	
Staining on - PL		4 - 5	
Staining on - PC		4	
Staining on - WO		4	



